

## Tehničko Uputstvo

### TU0003/00 BEZBOJNA POLIURETANSKA PODLOGA

Primena:	Ravne površine, profili		
Način korišćenja:	nalivanje i sprej		
Procedura mešanja:		težina (kg)	zapremina(l)
Komponenta A	TU0003/00	100	100
Komponenta B (učvršćivač)	TH0805/00	50	50
Rastvarač	DT1150/00	10-20	10-25

#### Tehničke karakteristike

Suva materija (%):	43 ± 1
Specifična težina (kg/l):	0.950 ± 0.030
Viskozitet (DIN 4 at 20°C):	60" ± 3"

#### Priprema podloge

Sa rastvaračima na vodenoj bazi (AC0600/XX ili AC1400/XX) ili sa razređivačima (XM7100/XX or XM8000/XX).

#### Osnovne karakteristike

Vreme eksploatacije od otvaranja:	3 sata
Poreporučena potrošnja (g/m <sup>2</sup> ):	Min. 80 - Maks. 150
Interval između nanošenja slojeva:	Min. 30' - Maks. 2 sata

**N.B.:** DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

**WARNING:** ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Broj slojeva:	Maksimum 4
Vreme sušenja (100 g/m <sup>2</sup> na 20°C):	Ne lepi se prašina 5'-10' Pritisak prstom ne ostavlja trag 30'-40' Može da se odloži 3 sata
Sušenje u tunelu sa pojačanom ventilacijom (100 g/m <sup>2</sup> ):	predsušenje 10' vruć vazduh 50°C 40' hlađenje 10'
Šmirglanje:	sačekati minimum 6 sati
Nanošenje novog sloja:	sačekati minimum 8 sati
Rok trajanja (meseci):	36 Nakon dužeg stajanja proizvoda uvek pre upotrebe proverite homogenost i radi eliminisanja taloga dobro promešajte pre upotrebe.

TU0003/00 je veoma svestran osnovni premaz sa odličnim karakteristikama.

Pokazuje veoma dobre osobine pri sušenju, šmirglanju i otpornosti.

### Upozorenje

U letnjem periodu kao i u jako toplim predelima, preporučujemo usporavanje procesa sušenja upotrebom DT1146/00.

Ukoliko je potrebno blago nijansiranje, preporučujemo upotrebu koncentrisane boje XC1900/XX.