

Tehničko Uputstvo

TU0223/13 BELA POLIURETANSKA OSNOVA

Primena:	Medijapan, ravne površine		
Način korišćenja:	Nalivanje i pištolj		
Procedura mešanja:	težina (kg) zapremina (l)		
Komponenta A:	TU0223/13	100	100
Komponenta B (učvršćivač):	TH0780/00	30	30
Razređivač:	DT1150/00	20-30	30-40

Tehničke karakteristike

Suva materija (%):	77 ± 2	
Specifična težina (kg/l):	1.511 ± 0.030	
Viskozitet (cps):	11.000 ± 1.000	
Vreme eksploatacije od otvaranja:	3 sata	
Preporučena gramaža za jedan sloj (g/m ²):	Maks. 150 za jedan sloj	
Vremenski interval između slojeva:	Min. 50' - Maks. 3 sata	
Broj slojeva:	Maksimum 3	
Vreme sušenja (100 g/m ² na 20°C):	Ne lepi se prašina	30'
	Pritisak prstom ne ostavlja trag	60'
	Može da se skladišti	5 sati
Šmirglanje:	Sačekati najmanje 8 sati.	

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Nanošenje sledećeg sloja:	Sačekati bar 12 sati. Nanesite PU ili NC pigmentisane završne boje.
Rok trajanja (meseci):	36 Nakon dužeg stajanja proizvoda uvek pre upotrebe proverite homogenost i dobro ga promešajte kako bi se eliminisalo eventualno taloženje.

Priprema podloge

Detaljno šmirglanje i čišćenje.

Osnovne karakteristike

TU0223/13 je otporan na slivanje, ima dobru pokrivnu moć i lako se šmirgla. Posebno je osmišljen da dobro pokriva površinu, a u isto vreme garantuje maksimalnu elastičnost. Pogodan je za korišćenje na iverici i poroznom masivnom drvetu koje zahteva visok nivo popunjavanja pora. Njegova finoća izrade je prilagođena za upotrebu kako bi se izbegli problemi sa filterima i diznama.

Alternativni učvršćivači

Za brže sušenje ali niži stepen elastičnosti koristite TH0713/00 na 30% težine i 50% zapremine.

Posebna upozorenja

Iako TU0223/13 ima visoku elastičnu moć očigledno je da nije u stanju da izdrži velika pomeranja podloge. Ovo se posebno odnosi na meku ivericu, deblje ploče medijapana ili furniranih panela. Potrebno je pre upotrebe izvršiti testiranje na manjoj površini kako bi bili sigurni da tretirana površina neće ispucati.

Obratite pažnju da ne prekoračite preporučenu debljinu sloja i da se koriste navedeni učvršćivači.