SAYERLACK
INNOVATIVE WOOD SOLUTIONS
Sayerlack is a brand of SHERWIN-WILLIAMS
SAYERLACK S.r.l. - With a Single Shareholder
Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770511 - fax +39 051 777437
www.sayerlack.it - www.lineabluvernici.it
Cod. Fisc. e Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200
R.E.A. n. 313180 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531
Company under the direction and coordination of The Sherwin-Williams Company, USA

„Drvo-art" d.o.o.
PREDUZEĆE ZA PROIZVODNJU, PROMET I USLUGE
32000 Čačak, Potes Ključ bb, Tel/Fax: +381 32 55 73 521, Tel: +381 32 55 75 168
E-mail: Prodaja: prodaja@drvo-art.com; Office: komercijala@drvo-art.com;
www.drvo-art.com

Tehničko **Uputstvo**

TU0271/13
VISOKO POKRIVAJUĆA PIGMENTISANA POLIURETANSKA PODLOGA

Boja:	13 bela
Primena:	Unutrašnji i spoljni delovi sklopivog nameštaja, ramovi, medijapan
Način nanošenja:	Pištolj
Procedura mešanja:	Prema težini (kg)
Komponenta A:	TU0271/13 100
Komponenta B (učvršćivač):	TH0780/00 40
Razređivač:	DT0436/00 10

Tehničke karakteristike

Suva materija (%):	72 ± 2
Specifična težina (kg/l):	1.450 ± 0.030
Viskozitet (na 20°C):	40" ± 3" (DIN 6)

Osnovne karakteristike

Rok trajanja nakon otvaranja na 20°C:	2 sata
Preporučena debljina sloja (g/m²):	maks.200 po sloju
Razmak između nanošenja:	min. 50' - maks. 4 sata
Broj slojeva:	maks. 3
Vreme sušenja (100 g/m² na 20°C):	Bez prašine 10' Suvo na dodir 35' Odlaganje 8 sati
Veštačko sušenje (100 g/m²):	ventilacija 15' vruć vazduh na 50°C 50' ventilacija 15'
Šmirglanje:	Sačekati najmanje 12 sati
Premazivanje:	Sačekati najmanje 12 sati Nanesite PU ili NC završne premaze.
Rok trajanja (u mesecima):	36 Nakon dužeg stajanja uvek proverite homogenost i dobro promešajte pre upotrebe kako bi izbegli moguću sedimentaciju.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Priprema podloge

Detaljno čišćenje i šmirglanje.

Osnovne karakteristike

TU0271/13 je osnovna podloga za ravne delove i profile koja pokazuje odlučnu pokrivnu moć in a oštrim ivicama, dobro prijanja in a vertikalnim osnovama kada se nanosi fiksnim pištoljem i odlično se šmirgla.

Upozorenje

Elastičnost TU0271/13 je visoka ali ne može da podnese preterano pomeranje do kod može doći kod korišćenja šperploče od mekih vrsta drveta, debljih medijapana ili furniranih panela. Preporučujemo da se uradi testiranje na željenoj površini kako bi videli da li dolazi do pucanja tj. Do pojave pukotina. Štaviše savetujemo da se ne prekoračuje preporučena debljina sloja kao id a se ne traži zamena za pomenuti učvršćivač.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.